FIREFORCE



PAG. 1/2

SIZE 36 - 47



NORMS EN ISO 20347:2012

02 - Closed heel area | Anti-static properties | Heel energy absorption | Water penetration and absorption

SRC - Slip resistance on ceramic + sodium lauryl sulfate and steel + glycerin

HRO - Resistance to hot contact of the outsole

WRU - Water penetration resistant uppers

ADVANTAGES

Comfortable | Fire station boots | Ideal for training

WORKING ENVIRONMENT

TRAINING | OCCURRENCES | FORMATIONS | FIRE STATIONS











PAG. 2/2 CERTIFICATION NUMBER

TECHNICAL INFORMATION

MATERIALS ST	TANDARDS	DESCRIPTION	UN.	RESULTS	REQ. EN ISO 15090:2012
UPPER Treated skin, soft and uniform, with excellent transpire characteristics that significantly increases the level of comfor Excellent resistance and durability.	5.4.6	WATER VAPOUR PERMEABILITY COEFFICIENT OF PERMEABILITY	mg/cm ² .h mg/cm ²	3,1 31	min. 2,0 min. 20
	5.4.3	TEARING STRENGTH TRANSMITED WATER AFTER 60 MI		245 0,0	min.120 max. 0,2 max. 30
	6.3	ABSORBE WATER AFTER 60 MIN	%	5,5	max. 3U
UPPER LINING 3D MESH-Does not create odors and with excellent breathability	6.6+6.8	WATER VAPOUR PERMEABILITY COEFFICIENT OFPERMEABILITY	mg/cm ²	32 256	min. 2 min. 20
	6.3	TEARING STRENGTH	N	32	min. 15
INSOCK PU COMFORT - Soft and light with anti-static points. Easy to remove for cleaning and drying.	6.2.1.1	ABRASION RESISTANCE (DRY) ABRASION RESISTANCE (WET) WATER ABSORPTION WATER DESORPTION	cycles cycles % mg/cm ²	no rupture no rupture - -	51.200 25.600 min. 70 min. 100
SOLE NITRILE RUBBER - resistance to high temperatures and greadurability. Anti-slip characteristics and resistance to hydrocarbons and oils.		TEARING STRENGTH ABRASION RESISTANCE SLIP RESISTANCE ON CERAMIC FLOOR WITH WATER AND DETERGENT SLIP RESISTANCE ON STEEL FLOOR WITH GLYCERINE	N/mm mm³ flat heel flat heel	16 100 0,47 0,42 0,22 0,16	min. 8 max. 150 min. 0,32 min. 0,28 min. 0,18 min. 0,13
SHOCK ABSORPTION - The absorption capacity of the impact when walking.	6.2.4	SHOCK ABSORPTION (HEEL)	J	103	min. 20

SHOE WEIGHT (SIZE 40): 590 GR



